

ALLEN® 5100WMG

Co-extruded, High Impact ASA/ABS, Medium Gloss Sheet

Introduction

ALLEN® 5100WMG is high impact ABS capped with medium gloss ASA for UV protection.

General Information

ALLEN® 5100WMG is Underwriters Laboratories, Inc® recognized for UL Std 94 HB (UL94) and Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302)

Suggested Applications

- Vehicle Exteriors
- Radomes
- Bus Hatches
- Sunroom Exteriors & Interiors
- Equipment Housings
- Marine dashes & components

Features

- Custom color matching
- Excellent UV properties
- Edge trim easily used into future orders
- Medium gloss finish

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed, and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001:2008 and 14001:2004 Certified

Customer Service

1305 Lincoln Ave. Holland MI 49423 USA

Phone: 800.823.1305

Outside the US: +1.616.394.3808

Fax: 800.832.5536, +1.616.394.3875

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

ALLEN® 5100WMG Co-extruded, High Impact ASA/ABS, Medium Gloss Sheet

Physical Properties

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.05	
Water Absorption, 24hr	ASTM D570	0.37%	
Rockwell Hardness, R-Scale	ASTM D785	98	
MECHANICAL			
Tensile Strength @ 23 °C (73 °F)	ASTM D638	5,840 psi	40.3 MPa
Tensile Modulus @ 23 °C (73 °F)	ASTM D638	287,000 psi	88.3 MPa
Flexural Modulus @ 23 °C (73 °F)	ASTM D790	296,000 psi	2040.8 MPa
Flexural Stress at 5% Strain @ 23 °C (73 °F)	ASTM D790	8,980 psi	61.9 MPa
Compressive Strength, yield	ASTM D695	7,080 psi	48.8 MPa
Shear Strength	ASTM D732	4,440 psi	30.6 MPa
Bearing Strength, 4% deflection	ASTM D953	2,930 psi	20.2 MPa
Bearing Strength, max.	ASTM D953	25,700 psi	177.2 MPa
Notched Izod Impact Resistance @ 23 °C (73 °F)	ASTM D256	7.31 ft-lbs/in	390 J/m
Gardner Drop Dart Impact, GE @ 23 °C (73 °F)	ASTM D5420	330 in-lbf	37.3 J
THERMAL			
Heat Deflection Temperature (HDT) @264psi (1.8MPa), annealed	ASTM D648	210.8 °F	99.4 °C
Heat Deflection Temperature (HDT) @66psi (0.45MPa), annealed	ASTM D648	215.5 °F	102 °C
Coefficient of Thermal Expansion (MD)	ASTM E831	52.6 µin/in/°F	94.7 µm/m/°C
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	459 V/mil	18.1 kV/mm
FLAMABILITY			
Underwriters Laboratories, Inc. [®] Component Recognition	UL Standard 94 HB	0.060 in	
Motor Vehicle Safety Standard	FMVSS 302	PASSES	
¹ Values based upon 0.125" (3.17mm) sheet unless otherwise specified Not intended for specification purposes.			

SEKISUI SPI

ISO 9001:2008 and 14001:2004 Certified

Customer Service

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305
Outside the US: +1.616.394.3808
Fax: 800.832.5536, +1.616.394.3875
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.