

KYDEX® 6565(d)

Decorative low heat release aviation sheet

Introduction

KYDEX® 6565(d) is a proprietary, high performance, decorative thermoplastic sheet specifically formulated to meet the safety needs of the aviation industry.

General Information

KYDEX® 6565(d) is a proprietary, high performance, decorative thermoplastic sheet that meets all fire retardancy requirements set forth in Federal Aviation Regulations 25.853 paragraphs (a) and (d) including low heat release (65 / 65) in the OSU rate of heat release test. Its excellent properties make it the ideal material to form two-and-three-dimensional aircraft components.

Suggested Applications

- Seat parts
- Window shades
- Life vest shrouds
- Passenger service units
- Monitor shrouds
- Bulkhead laminates
- Armrests
- Moulding strips
- Tray tables
- Kick panels

Features

- Available in a wide range of thicknesses, enabling you to satisfy both the functional and aesthetic requirements of any aircraft interior.
- Very resistant to a wide range of concentrate chemicals, and is therefore easy to clean with standard household cleaning agents excluding abrasive and concentrated products
- Meets the stringent requirements of the FAR 25.853(a) and(d) in all thicknesses and colours.
- Forms to deep draws with low forces when heated to the upper end of the proper forming temperature range
- Crisp detail is achieved and rejects are minimized
- Can be formed on all standard presses and cut on all standard die-cutting machines
- Secondary operations include: machining, sawing, blanking, punching, etc. are easily performed

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Material Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® 6565(d)

Decorative low heat release aviation sheet

Physical Properties

Property	Test Method	Typical Value ¹	
Specific Gravity	ASTM D-792	1.52	
Tensile Strength	ASTM D-638	43 MPa	6,200 psi
Flexural Strength	ASTM D-790	81.2 MPa	11,780 psi
Modulus of Elasticity	ASTM D-790	3,833 MPa	556,000 psi
Rockwell Hardness (R Scale)	ASTM D-785	111	
Heat Deflection Temperature (HDT) @ 1.8 MPa (264 psi) annealed	ASTM D-648	75.9°C	168.6°F
Flammability: Vertical Burn, 60-second Vertical Burn, 12-second	FAR 25.853 (a)(i) FAR 25.853 (a)(ii)	PASS PASS	
Flammability: OSU Heat Release	FAR 25.853 (d) Part IV	Total: <65 kw-min/m ² Total: <65 kw/m ²	
Flammability: NBS Smoke Density	FAR 25.853(d) Part V	D max <200	
Forming Temperature		163 - 200°C	325 - 390°F
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
 techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.