

KYDEX® V Utility sheet

Introduction

KYDEX® V sheet is a recycled grade of a proprietary thermoplastic sheet that is cost competitive with other grades of thermoplastic sheet while offering improved performance.

General Information

KYDEX® V is particularly well suited for hidden or painted parts since it has some degree of color variability. It is only available in Black (52114), in thicknesses from 1.00mm (0.040") and up, and in a limited number of textures.

Suggested Applications

- Equipment Housings
- Miscellaneous Applications

Features

- Offered in thicknesses 0.71mm (0.028") and up
- Available in rollstock at 1.00mm (0.040") and in sheet stock in all thicknesses
- Available in black only
- Available in 7 distinctive textures
- Excellent forming properties, uniform wall thicknesses and crisp detail
- Easy machining and fabricating using conventional methods and equipment

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Material Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® V Utility sheet

Physical Properties

| Property | Test Method | Typical Value ¹ | |
|--|-------------|----------------------------|-------------|
| Specific Gravity | ASTM D-792 | 1.35 | |
| Tensile Strength | ASTM D-638 | 42 MPa | 6,100 psi |
| Flexural Strength | ASTM D-790 | 63 MPa | 9,100 psi |
| Modulus of Elasticity | ASTM D-790 | 2,308 MPa | 335,000 psi |
| Notched Izod Impact Resistance, @ 23°C (73°F) | ASTM D-256 | 427 J/m | 8 ft-lbs/in |
| Rockwell Hardness (R Scale) | ASTM D-785 | 88 | |
| Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed | ASTM D-648 | 73.9°C | 165°F |
| Thermoforming Range | | 163 - 200°C | 325 - 392°F |
| Mold Shrinkage % (male mold) | | 0.40 - 0.60 | |
| ¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. Not intended for specification purposes. | | | |

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.