

KYDEX® 6565HI

High impact, low heat release aviation sheet

Introduction

KYDEX® 6565HI is a proprietary, high performance thermoplastic sheet with integral colour specifically engineered to improve aircraft passenger safety.

General Information

KYDEX® 6565HI was designed to provide material deformation when used in components subjected to the HIC Test (Head Injury Criterion) for increased passenger safety. It meets flammability and smoke development requirements outlined in Federal Aviation Regulations FAR 25.853 paragraphs (a) and (d).

Suggested Applications

- Seat parts
- Seatback shells
- Tray tables
- Monitor shrouds
- Bulkhead laminates

Features

- Improved impact properties over traditional thermoplastics for HIC compliance seating requirements
- Reduces cost of compliance by decreasing the total number of expensive and time consuming 16g tests required
- Increases design freedom to create more complex seat geometries
- Decreases weight by eliminating the need for heavy reinforcements or thick gauges
- Meets the stringent requirements of FAR 25.853 paragraphs (a) and (d) in all thicknesses and colours
- Excellent formability and fabrication characteristics
- Processes similar to KYDEX® 6565
- Allows for tight tolerance control
- Available in a wide range of integral colours

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001:2008 and 14001:2004 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® 6565HI

High impact, low heat release aviation sheet

Physical Properties

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.46	
Water Absorption, 24hr	ASTM D570	0.06%	
Rockwell Hardness, R-Scale	ASTM D785	100	
MECHANICAL			
Tensile Strength	ASTM D638	42.3 MPa	6,130 psi
Tensile Modulus	ASTM D638	2,723 MPa	395,000 psi
Poisson's Ratio	ASTM D638	0.397	
Flexural Strength	ASTM D790	66.7 MPa	9,680 psi
Flexural Modulus	ASTM D790	2,751 MPa	399,000 psi
Compressive Strength, yield	ASTM D695	55.6 MPa	8,070 psi
Compressive Modulus	ASTM D695	2,772 MPa	402,000 psi
Shear Strength	ASTM D732	46.0 MPa	6,670 psi
Bearing Strength, 4% deflection	ASTM D953	38.0 MPa	5,510 psi
Bearing Strength, max.	ASTM D953	187.5 MPa	27,200 psi
Gardner Drop Dart Impact, GE	ASTM D5420	69.8 J	618 in-lb _f
Puncture Energy, 3.3 m/s	ASTM D3763	43.0 J	31.7 ft-lb _f
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa), annealed	ASTM D648	75.3°C	168°F
Coefficient of Thermal Expansion	ASTM E831	68.5 μm/m/°C	38.0 μin/in/°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	18.9 kV/mm	480 V/mil
FLAMABILITY²			
Vertical Burn, 60-second	FAR 25.853(a)(i)	PASS	
Vertical Burn, 12-second	FAR 25.853(a)(ii)	PASS	
OSU Heat Release	FAR 25.853(d) Part IV	PASS	
NBS Smoke Density	FAR 25.853(d) Part V	PASS	
¹ Values based upon 3.20mm (0.125") sheet unless otherwise specified. ² All thicknesses Not intended for specification purposes.			

SEKISUI SPI

ISO 9001:2008 and 14001:2004 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.