

KYDEX® 7200ST

Smoke and toxicity compliant aviation sheet

Introduction

KYDEX® 7200ST is a high performance thermoplastic sheet designed for use in aviation interior applications where smoke and ABD0031 or BSS7239 toxicity compliance is required.

General Information

KYDEX® 7200ST meets the flammability and smoke development requirements set forth in Federal Aviation Regulations (FAR) 25.853 paragraphs (a) and (d) Part V as well as the toxicity requirements for Airbus (ABD0031) and Boeing (BSS7239). Its wide processing window and ease of thermoforming makes it ideal for complex parts.

Suggested Applications

- Armrests
- Tray tables
- Kick panels
- Trim parts

Features

- Meets flammability and smoke development requirements listed in FAR 25.853(a) and (d) Part V
- Compliant to ABD0031 and BSS7239 toxicity specifications
- Excellent formability and fabrication characteristics
- Allows for tight tolerance control
- Available in P3 – Velour Matte in thicknesses from 1.19mm to 4.75mm (0.047" to 0.187")

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Material Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® 7200ST

Smoke and toxicity compliant aviation sheet

Physical Properties

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D-792	1.25	
Water Absorption, 24hr	ASTM D-570	0.16%	
Rockwell Hardness, R-Scale	ASTM D-785	112	
MECHANICAL			
Tensile Strength	ASTM D-638	53.5 MPa	7,760 psi
Tensile Modulus	ASTM D-638	2,868 MPa	416,000 psi
Flexural Strength	ASTM D-790	87.6 MPa	12,700 psi
Flexural Modulus	ASTM D-790	2,758 MPa	400,000 psi
Compressive Strength, yield	ASTM D-695	73.1 MPa	10,600 psi
Compressive Modulus	ASTM D-695	2,718 MPa	394,000 psi
Shear Strength	ASTM D-732	45.5 MPa	6,600 psi
Bearing Strength, 4% deflection	ASTM D-953	27.6 MPa	4,000 psi
Bearing Strength, max.	ASTM D-953	246 MPa	35,700 psi
Gardner Drop Dart Impact, GE	ASTM D-5420	46.9 J	415 in-lb _i
THERMAL			
Heat Deflection Temperature (HDT) @ 264psi (1.8 MPa) unannealed/annealed	ASTM D-648	100°C	212°F
Coefficient of Thermal Expansion	ASTM E-831	51.4 μm/m/°C	28.6 μin/in/°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D-149	23.8 kV/mm	605 V/mil
FLAMABILITY²			
Vertical Burn, 60-second	FAR 25.853(a)(i)	PASS	
Vertical Burn, 12-second	FAR 25.853(a)(ii)	PASS	
NBS Smoke Density	FAR 25.853(d) Part V	D _{max} <200	
Airbus Toxic Gas Generation	ABD-0031	PASS	
Boeing Toxic Gas Generation	BSS 7239	PASS	
¹ Values based upon 0.125" (3.17mm) sheet unless otherwise specified ² All Thicknesses Not intended for specification purposes.			

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
 techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.