

## ALLEN® 2180HG High Impact ABS, High Gloss Sheet

### Introduction

ALLEN® 2180HG is a general purpose ABS that has high impact strength and a good cost to performance ratio to other materials like stainless steel, and other thermoplastics.

### General Information

ALLEN® 2180HG has been tested under laboratory conditions and has achieved a UL94 HB rating at 0.060 in (1.52mm) and above and meets the requirements of Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302).

### Suggested Applications

- Mechanical covers & housings
- Beverages dispensers
- Food equipment housings

### Features

- Custom color matching
- Good forming properties
- Edge trim easily used in future orders
- High gloss, high impact
- Excellent low temperature performance

### Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed, and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Safety Data Sheets, please call 800.325.3133.

#### SEKISUI SPI

##### Customer Service

1305 Lincoln Ave. Holland MI 49423 USA  
Phone: 800.823.1305  
Outside the US: +1.616.394.3808  
Fax: 800.832.5536, +1.616.394.3875  
Email: [info@sekisui-spi.com](mailto:info@sekisui-spi.com)

##### Technical Service

Phone: 800.682.8758  
Fax: +1.570.387.8722  
Outside the US: +1.570.387.6997  
[techservice@sekisui-spi.com](mailto:techservice@sekisui-spi.com)

[sekisui-spi.com](http://sekisui-spi.com)

## ALLEN® 2180HG High Impact ABS, High Gloss Sheet

### Physical Properties

Property	Test Method	Typical Value <sup>1</sup>	
<b>PHYSICAL</b>			
Specific Gravity	ASTM D792	1.06	
Water Absorption, 24 hr	ASTM D570	0.28%	
Rockwell Hardness, R-Scale	ASTM D785	98	
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	5,330 psi	36.7 MPa
Tensile Modulus	ASTM D638	293,000 psi	2,020.2 MPa
Flexural Modulus	ASTM D790	307,000 psi	2,116.7 MPa
Flexural Stress at 5% Strain	ASTM D790	8,920 psi	61.5 MPa
Compressive Strength	ASTM D695	7,190 psi	49.6 MPa
Shear Strength	ASTM D732	5,810 psi	40.1 MPa
Bearing Strength, 4% deflection	ASTM D953	4,040 psi	180.6 MPa
Bearing Strength, max.	ASTM D953	26,200 psi	358.8 J/m
Notched Izod Impact	ASTM D256	6.72 ft-lb/in	432 J/m
Gardner Drop Dart Impact, GE	ASTM D5420	301 in-lbf	34.0 J
<b>THERMAL</b>			
Heat Deflection Temperature (HDT) @264 psi (1.8 MPa), annealed	ASTM D648	211.7 °F	99.9 °C
Heat Deflection Temperature (HDT) @66 psi (0.45 MPa), annealed	ASTM D648	219.1 °F	104 °C
Coefficient of Thermal Expansion (MD)	ASTM E831	50.1 µin/in/°F	90.1 µm/m/°C
<b>ELECTRICAL</b>			
Dielectric Strength, oil	ASTM D149	442 V/mil	17.4 kV/mm
<b>FLAMMABILITY</b>			
Underwriters Laboratories, Inc. <sup>®</sup> Component Recognition	UL Standard 94 <sup>2</sup>	HB @ 0.060 in (1.52mm)	
Motor Vehicle Safety Standard	FMVSS 302	PASS	

<sup>1</sup> Values based upon injection molded resin.

<sup>2</sup> ALLEN® 2180HG has been tested under laboratory conditions and has passed UL 94HB criteria. SEKISUI SPI makes no warranty or guarantee that these products will meet UL 94HB in the parts final, finished configuration.  
Not intended for specification purposes.

### SEKISUI SPI

#### Customer Service

1305 Lincoln Ave. Holland MI 49423 USA  
Phone: 800.823.1305  
Outside the US: +1.616.394.3808  
Fax: 800.832.5536, +1.616.394.3875  
Email: info@sekisui-spi.com

#### Technical Service

Phone: 800.682.8758  
Fax: +1.570.387.8722  
Outside the US: +1.570.387.6997  
techservice@sekisui-spi.com

[sekisui-spi.com](http://sekisui-spi.com)

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.