

ALLEN® 6010M

Triple Layer Coextruded, Acrylic Capped, Medium Impact ABS, Low Gloss Sheet

Introduction

ALLEN® 6010M is low gloss acrylic capped ABS with medium impact, excellent outdoor weathering, and durability.

General Information

ALLEN® 6010M has been tested under laboratory conditions and has achieved a UL94 HB rating at 0.060 in (1.52mm) and above and meets the requirements of Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302).

Suggested Applications

- Lawn and Garden Equipment
- Marine Parts
- Heavy Equipment Exteriors
- Recreational Vehicles
- Kayaks

Features

- Custom color matching
- UV protection
- Good abrasion resistance
- Low gloss finish
- Excellent color and gloss retention
- Good chemical resistance

Environmental and Safety Considerations

SEKISUI SPI is committed to ensuring that its products can be manufactured, transported, stored, used, disposed, and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.sekisui-spi.com>. For Safety Data Sheets, please call 800.325.3133.

SEKISUI SPI

Customer Service

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305
Outside the US: +1.616.394.3808
Fax: 800.832.5536, +1.616.394.3875
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

ALLEN® 6010M

Triple Layer Coextruded, Acrylic Capped, Medium Impact ABS, Low Gloss Sheet

Physical Properties

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.06	
Water Absorption, 24 hr	ASTM D570	0.28%	
Rockwell Hardness, R-Scale	ASTM D785	98	
MECHANICAL			
Tensile Strength	ASTM D638	5,330 psi	36.7 MPa
Tensile Modulus	ASTM D638	293,000 psi	2,020.2 MPa
Flexural Modulus	ASTM D790	307,000 psi	2,116.7 MPa
Flexural Stress at 5% Strain	ASTM D790	8,920 psi	61.5 MPa
Compressive Strength	ASTM D695	7,190 psi	49.6 MPa
Shear Strength	ASTM D732	5,810 psi	40.1 MPa
Bearing Strength, 4% deflection	ASTM D953	4,040 psi	180.6 MPa
Bearing Strength, max.	ASTM D953	26,200 psi	358.8 J/m
Notched Izod Impact	ASTM D256	6.72 ft-lb/in	432 J/m
Gardner Drop Dart Impact, GE	ASTM D5420	301 in-lbf	34.0 J
THERMAL			
Heat Deflection Temperature (HDT) @264 psi (1.8 MPa), annealed	ASTM D648	211.7 °F	99.9 °C
Heat Deflection Temperature (HDT) @66 psi (0.45 MPa), annealed	ASTM D648	219.1 °F	104 °C
Coefficient of Thermal Expansion (MD)	ASTM E831	50.1 µin/in/°F	90.1 µm/m/°C
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	442 V/mil	17.4 kV/mm
FLAMMABILITY			
Underwriters Laboratories, Inc. [®] Component Recognition	UL Standard 94 ²	HB @ 0.060 in (1.52mm)	
Motor Vehicle Safety Standard	FMVSS 302	PASS	

¹ Values based upon injection molded resin.

² ALLEN® 6010M has been tested under laboratory conditions and has passed UL 94HB criteria. SEKISUI SPI makes no warranty or guarantee that these products will meet UL 94HB in the part's final, finished configuration.
Not intended for specification purposes.

SEKISUI SPI

Customer Service

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305
Outside the US: +1.616.394.3808
Fax: 800.832.5536, +1.616.394.3875
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

[sekisui-spi.com](http://www.sekisui-spi.com)

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.