

Cleaning KYDEX® Sheet

TB - 160-A

General Information

KYDEX® sheet will retain its original beauty with reasonable handling and care. To ensure that your part maintains its original appearance, please review the following guidelines.

To clean KYDEX® sheet, dust it with a soft, damp cloth or chamois and wipe the surface gently. Use soap and lukewarm water to remove light dirt. After washing and rinsing, be sure to dry the surface by blotting with a damp cloth or chamois to prevent streaking and water spots.

For general (routine) cleaning, the following mild detergents and multi-purpose cleaners are recommended:

- Top Job with Ammonia
- Joy Detergent
- Janitor in a Drum
- Isopropanol
- Spic & Span
- Fantastik
- Formula 409
- All Detergent (Powder)
- Johnson's Pledge
- Mr. Clean
- Cascade

Normal cleaning methods may not remove ground in dirt or grease. To remove dirt or grease from texture valleys, a short stiff bristled brush should be used to loosen the material followed by a water rinse.

Cleaners Not Recommended

- Wisk
- Lestoil
- Meguiar's Carpet
- Kerosene
- Cold Power Liquid
- Pine Sol
- Gasoline
- Liquid All
- Abrasives
- Methanol
- Isopar K
- Endust
- Tetrahydrofuran
- Brake Fluid
- Dynamo
- Ketones
- Johnson's Pride
- Hexane

- Goof-Off "The Miracle Cleaner" by W.M. Barr & Co.

NOTE: The chemical composition of Goof-Off has recently been reformulated. This new formulation has been observed to have an affect on KYDEX® sheet. The previous formulation may be identified by the phrase "The Professional Cleaner" on the can and is produced by Valspar. This formulation is still recommended for use on KYDEX® sheet. The new formulation may be identified by the phrase "The Miracle Cleaner" on the can and is produced by W.M Barr & Co. SEKISUI SPI is investigating suitable alternatives to the Goof-Off product.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Outside the US: +1.570.389.5814
 Fax: 800.452.0155, +1.570.387.7786
 Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
 Fax: +1.570.387.8722
 Outside the US: +1.570.387.6997
 techservice@sekisui-spi.com

sekisui-spi.com

Cleaning KYDEX® Sheet

TB - 160-A

In-Use Spot Cleaning

For More Information on In-Use Spot Cleaners:

Product and Manufacturer	On the Web	In US Call
"Goof-Off Professional" by Valspar	www.goof-off.com	800.345.4530
"Goof-Off Graffiti Remover"	www.goof-off.com	800.345.4530
"DWR-II" by Chemique	www.chemique.com	800.225.4161
"Write Away" by Zep	www.zepmfg.com	877.428.9937
"Goo-Gone" Spray Gel	www.GooGone.com	800.328.9248

In-House Test Results

	ArmorAll ¹		Goof-Off Professional ²		Goof-Off Graffiti Remover ³		Goo-Gone Spray Gel ⁴		Fantastik Orange Action ⁵	
	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep
Texture	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep	Smooth	P1 Deep
Pen Ink	No	No	Yes	Yes	Yes	Yes	Very Faded	Very Faded	Faded	No
Marker	Faded	No	Yes	Visible	Yes	Yes	Very Faded	No	Faded	No
Crayon	Yes	No	Yes	Yes	Yes	Yes	Yes	Yes	No	No
Spray Paint	No	No	Yes	Yes	Yes	Yes	Some	No	No	No

Note: To remove graffiti from deeper textures a bristle brush must be used. Several applications were also necessary. A soft bristle brush would be best because excess scrubbing could flatten, or dull the surface texture.

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Outside the US: +1.570.389.5814

Fax: 800.452.0155, +1.570.387.7786

Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758

Fax: +1.570.387.8722

Outside the US: +1.570.387.6997

techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.